

FRT - FLAME RETARDANT CABLE AND CONDUIT TAGS

Flame Retardant Cable Tags are made of a thermoplastic polyether-polyurethane material, which is a halogen free, flame retardant, hydrolysis and microorganism resistant material. These tags are constructed in a one material make-up, making them extremely durable and able to hold up to most elements. They are used for identification of cables, conduits and wires. The tags are supplied on a roll with a perforated carrier for easy removal.

FEATURES

- RoHS compliant
- Tear resistant
- Raw material fulfills UL94-V0

COLORS

- White
- Yellow
- Orange
- Red
- Green
- Other colors available



MATERIAL

- Thermoplastic Polyether- Polyurethane (PUR)

OPERATING TEMP

- -50°C up to +100°C. Peak +125°C / -58°F up to 212°F. Peak 257°F

SPECIFICATIONS

- Adherence: MIL81531 (SAEAS81531-1998 Clause 3.4.2/4.6.2)
- Resistance to solvents:
- MIL-STD-202G test method 215(2002)
- (MIL81531/SAE-AS81531-1998 Clause 3.4.3.)

STORAGE

- Cool and dry in original packaging

FRT - FLAME RETARDANT CABLE AND CONDUIT TAGS

Technical Data

DIMENSIONAL DATA

Product Code	Part Number	Color	Size	Qty/Roll
522	FRT 047 x 236-W	White	0.47" x 2.36"	1000
523	FRT 050 x 300-W	White	0.50" x 3.00"	1100
524	FRT 100 x 300-W	White	1.00" x 3.00"	550
522	FRT 047 x 236-Y	Yellow	0.47" x 2.36"	550
523	FRT 050 x 300-Y	Yellow	0.50" x 3.00"	550
524	FRT 100 x 300-Y	Yellow	1.00" x 3.00"	300

PHYSICAL DATA

Properties	Test Method	Typical Value
Hardness	DIN 53505	58 Shore D
Density	DIN 53479	1.27 g/cm ³
Tensile Strength	DIN 53504	30 MPa
Elongation at break	DIN53504	400%
Stress at 20% elongation	DIN 53504	13 MPa
Stress at 100% elongation	DIN 53504	19 MPa
Stress at 300% elongation	DIN 53504	33 MPa
Tear Strength	DIN 53515	110 N/mm
Abrasion Loss	DIN 53516	30 mm ³
Compression set at room temperature	DIN EN ISO 815	30%
Compression set at 70° C	DIN EN ISO 815	45%
Tensile Strength after storage in water at 80° C for 42 days	DIN 53504	20 MPa
Elongation at break after storage in water at 80° C for 42 days	DIN 53504	400%
Notched impact strength (Charpy) +23° C	DIN EN ISO 179	50 kJ/m ²
Notched impact strength (Charpy) - 30° C	DIN EN ISA 179	3 kJ/m ²

The indicated values are representative values.

FRT - FLAME RETARDANT CABLE AND CONDUIT TAGS

Technical Data

THERMAL DATA

Properties	Test Method	Typical Value
Glass transition temperature, 10°C/min	ISO 11357-1/-2	-44° C
Burning behaviour at 0.75 mm nom thickness	UL94	Class V-2
Burning behavior at 3.0 mm thickness	UL94	Class V-0
Oxygen Index	ISO 4589-1/-2	24%

UV STABILITY DATA

Results of accelerated aging testing are as a result of artificial lighting/illumination in a laboratory. Duration of test is 500 hours, which equals 10 years of exposure.

Properties	Test Method	Typical Value
UV-A 340 nm 500 hours Light 60 ° irradiation 0.76 W/m ² power duration 8 hours - Spray duration 15 min. - Condensation 50 ° duration 3,45 hour.	Visual Inspection	No creasing or cracking
	Mark Adherence	Good contrast and visibility

Properties	Test Method	Typical Value
TEST with XENON lamp, 500 hours XENON (340nm) - Light 65 ° c irradiation 0.50 W/m ² duration 1,42 hours - Light + Spray duration 0.60 W/m ² duration 18 min	Visual Inspection	No creasing or cracking
	Mark Adherence	Good contrast and visibility

FRT - FLAME RETARDANT CABLE AND CONDUIT TAGS

Chemical Properties

CHEMICAL RESISTANCE

Solvents Resistance

No degradation of the CMX TPU products occurs, however, according to the solvent class a variable degree of swelling and consequent reduction in tensile strength (after evaporation of the solvents, the tensile strength recovers approx. its original value).

Methanol should be considered more as a chemical reagent than as a solvent. TPU is soluble in some solvents. As test procedure, 5A test rods (DIN EN ISO 527-2) were immersed in the solvent for three weeks at 23° C, and tested for tensile strength are rounded values.

Code	Test Fluid	Swelling	Reduction of Tensile Strength %
Aliphatic	Pentan	10	20
Hydrocarbons	Cyclohexan	22	10
	Isooctan	7.5	none

Impact, Inc.'s polyether-polyurethane FRT tags behave similarly in other aliphatic and cyclo-aliphatic hydrocarbons such as methane, ethane, propane, butane, hexane, octane, petroleum ether, paraffin oil, diesel oil and kerosine (although additives can present problems).

Aromatic Hydrocarbons	Toulene	65	50
-----------------------	---------	----	----

Other aromatic hydrocarbons such as benzene and xylene have a similar affect.

Aliphatic Esters	Ethyl Acetate	70	75
------------------	---------------	----	----

Other short-chained esters such as butyl acetate and amy acetate have a similar affect.

Aliphatic Ketones	Methyl Ethyl Ketone	130	90
-------------------	---------------------	-----	----

Other short-chained aliphatic ketones such as acetone and methyl isobutyl ketone = MIBK have a simiar affect

Aliphatic	MethylEthyle Chloride	190	95
Halogenated	Chloroform		Practically dissolved
Hydrocarbons	Tetrachloroethylene	75	54
1 C-atom			
1 C- atom and higher	Trichloroethane*		

* Other aliphatic halogenated hydrocarbons with 2 C-atoms and higher have a similar affect.

Aromatic	Chlorobenzene	110	60
Halogenated			
Hydrocarbons			

Other aromatic halogenated hydrocarbons have a similar affect.

FRT - FLAME RETARDANT CABLE AND CONDUIT TAGS

Chemical Properties

Code	Test Fluid	Swelling	Reduction of Tensile Strength %
ASTM - Oils acc. to ASTM D 471-06**	IRM 901 at 100 °C 500h	1	6
	IRM 901 at 100 °C 1000h	1	14
	IRM 902 at 100 °C 500h	9	4
	IRM 902 at 100 °C 1000h	10	5
Agents Dissolving TPU	IRM 903 at 100 °C 500h	18	8
	IRM 903 at 100 °C 1000h	20	30
	Tetrahydrofurane Dimethyl Formamide (DMF)	dissolved dissolved	dissolved dissolved
Alcohols and Fuels	Dimethyl Acetamide N-Methyl Pyrrolidone (NMP)	dissolved dissolved	dissolved dissolved
	Dimethyl Sulphoxide (DMSO) Pyridine	dissolved dissolved	dissolved dissolved
	Methanol Ethanol	28 33	6 14
FAM Test Fluids acc. to DIN 51 604*	Iso-Propanol Benzyl Alcohol	30 not measureable	4 partly dissolved
	Ethylen Glycol Glycerine	4 none	15 none
	Test Fluid A Test Fluid B Test Fluid C	67 68 43	60 74 70
Diesel Fuel Biodiesel Fuel RME @ 60°C	Diesel Fuel Biodiesel Fuel	11 27	none 21

FRT - FLAME RETARDANT CABLE AND CONDUIT TAGS

Chemical Properties

Code	Test Fluid	Swelling	Reduction of Tensile Strength %
Fuel Types ASTM D 471	Fuel A = Iso-Octane	7.5	none
	Fuel B = Iso-Octane Toluene 70% / 30%	25	36
	Fuel C = Iso-Octane Toluene 50% / 50%	38	44
	Fuel D = Iso-Octane Toluene 60% / 40%	31	44

* DIN 51 604, 03.1984, is the standard, established by FAM to assess the resistance of plastic materials to automotive fuels.

** The IRM reference oils are mineral oils with different paraffin and aromatics contents. The formerly used ASTM oils 1, 2 and 3 were replaced by the IRM oils 1, 2 and 3 owing to health risks, and are no longer available. The IRM oils 1, 2 and 3 are very similar in terms of their characteristics, but not identical. (FAM = Fachausschuß Mineral- und Brennstoffnormung-Professional committee for standardization of fuel stuffs) (ASTM = American Society for Testing and Materials)

Test fluid A consists of:
50.0 % by volume toluene
30.0 % by volume iso-octane
15.0 % by volume di-isobutylene
5.0 % by volume ethanol

Test fluid B consists of:
42.0 % by volume toluene
25.5 % by volume iso-octane
13.0 % by volume di-isobutylene
15.0 % by volume methanol
4.0 % by volume ethanol
0.5 % by volume water

Test fluid C consists of:
20.0 % by volume toluene
12.0 % by volume iso-octane
6.0 % by volume di-isobutylene
58.0 % by volume methanol
2.0 % by volume ethanol
2.0 % by volume water



CONTACT US

Tel. 425.656.0330

Fax 425.656.0440

sales@impactwiremarking.com

www.impactwiremarking.com

P.O. Box 88068 Seattle, WA 98138

This information and data is believed to be accurate and reliable. Although the information and recommendations set forth herein are presented in good faith and believed to be correct as of this date, Impact, Inc. makes no representations as to the completeness or accuracy thereof. We place at your disposal the technical information necessary for the correct use of our products. As conditions and methods of use are beyond our control, that the person receiving the same will make their own determination as to the suitability for their purpose. We reserve the right to modify characteristics with the aim of improving the product and adapting it to the requirements of the market.

We are not affiliated or endorsed by Impact Label Corporation (800.820.0362)